Report No:SCEPL/MT/May/28/01/01/2020-21 Date:23.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/May28/01
Source of Sample:	Samples supplied by the Customer
Agency	KIRDL
Date of Receipt:	28.05.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	May/26/01-16	26.05.2020	23.06.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.12
	May/26/01-17	26.05.2020	23.06.2020	150.0	149.9	150.0	22485	8.100	680.7	30.27	
	May/26/01-18	26.05.2020	23.06.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
2	May/26/01-19	26.05.2020	23.06.2020	150.0	150.0	149.9	22500	8.050	669.9	29.77	29.84
	May/26/01-20	26.05.2020	23.06.2020	150.0	149.9	150.0	22485	8.100	672.7	29.92	
	May/26/01-21	26.05.2020	23.06.2020	149.9	150.0	149.8	22485	8.250	670.5	29.82	
3	May/26/01-22	26.05.2020	23.06.2020	150.0	150.0	149.9	22500	8.050	670.9	29.82	30.13
	May/26/01-23	26.05.2020	23.06.2020	150.0	149.9	150.0	22485	8.100	692.7	30.81	
	May/26/01-24	26.05.2020	23.06.2020	149.9	150.0	149.8	22485	8.250	669.5	29.78	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

CONSULTIG ENGINEE Bangalore

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli Bangalore-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama8@gmail.com

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/May/28/01/01/2020-21 Date:23.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/May/28/02
Source of Sample:	Samples supplied by the Customer
Agency	KIRDL
Date of Receipt:	28.05.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
4	May/26/01-25	26.05.2020	23.06.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.12
	May/26/01-26	26.05.2020	23.06.2020	150.0	149.9	150.0	22485	8.100	680.7	30.27	
	May/26/01-27	26.05.2020	23.06.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
5	May/26/01-28	26.05.2020	23.06.2020	150.0	150.0	149.9	22500	8.050	669.9	29.77	29.84
	May/26/01-29	26.05.2020	23.06.2020	150.0	149.9	150.0	22485	8.100	672.7	29.92	
	May/26/01-30	26.05.2020	23.06.2020	149.9	150.0	149.8	22485	8.250	670.5	29.82	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

BVH CONSULTING ENGINEERS Pvt Ltd Bangalore

Suvetha-XII
AE LSD

Page 1/1

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/02/01/01/2020-21 **Date:07.06.2020**

TEST REPORT

***Client Name& Address:**	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
***Name of Work:**	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
***Letter Reference:**	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/02/01
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	02.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
***Grade of concrete**	M30
***Location**	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	May/31/01-01	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	445.9	19.82	19.43
	May/31/01-02	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	426.7	18.98	
	May/31/01-03	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	438.5	19.50	
2	May/31/01-04	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	455.9	20.26	20.03
	May/31/01-05	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	441.7	19.64	
	May/31/01-06	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	453.5	20.17	
3	May/31/01-07	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	464.9	20.66	20.31
	May/31/01-08	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	456.7	20.31	
	May/31/01-09	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	448.5	19.95	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA CONSULTING ENGINEERS PVT. LTD. Bangalore

Authorized Signatory

CONSULTING ENGINEERS PVT. LTD. Bangalore

Sreenivasa N L
AE&IO

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli Bangalore-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama8@gmail.com

Scanned with CamScanner

Report No:SCEPL/MT/Jun/02/01/01/2020-21 Date:07.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/02/02
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	02.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
4	May/31/01-10	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	445.9	19.82	19.43
	May/31/01-11	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	426.7	18.98	
	May/31/01-12	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	438.5	19.50	
5	May/31/01-13	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	455.9	20.26	20.03
	May/31/01-14	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	441.7	19.64	
	May/31/01-15	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	453.5	20.17	

Remarks:-

The results pertain to the samples received and tested.
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate
* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

AE/JD

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama8[illegible]@gmail.com |

Scanned with CamScanner

Report No:SCEPL/MT/Jun/02/01/01/2020-21 **Date:28.06.2020**

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/02/01
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	02.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	May/31/01-16	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.12
	May/31/01-17	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	680.7	30.27	
	May/31/01-18	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
2	May/31/01-19	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	669.9	29.77	29.84
	May/31/01-20	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	672.7	29.92	
	May/31/01-21	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	670.5	29.82	
3	May/31/01-22	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	670.9	29.82	30.13
	May/31/01-23	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	692.7	30.81	
	May/31/01-24	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	669.5	29.78	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA CONSULTIG ENGINEER PVT LTD Bangalore

Suvetha NK AE WO

SHIPRAMA Consulting Engineers PVT. LTD. Bangalore

Authorized Signatory

Assistant Executive Engineer Vidyaranyapura Sub Division BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/02/01/01/2020-21 **Date:28.06.2020**

TEST REPORT

***Client Name& Address:**	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
***Name of Work:**	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
***Letter Reference:**	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/02/02
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	02.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
***Grade of concrete**	M30
***Location**	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
4	May/31/01-25	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.12
	May/31/01-26	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	680.7	30.27	
	May/31/01-27	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
5	May/31/01-28	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	670.9	29.82	30.13
	May/31/01-29	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	692.7	30.81	
	May/31/01-30	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	669.5	29.78	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

CONSULTING ENGINEER BANGALORE Bangalore

Suretha .N.L
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli Bangalore-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama88@gmail.com

Scanned with CamScanner

Report No:SCEPL/MT/Jun/05/01/01/2020-21 **Date:09.06.2020**

TEST REPORT

***Client Name& Address:**	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
***Name of Work:**	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
***Letter Reference:**	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/05/01
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	05.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
***Grade of concrete**	M30
***Location**	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	Jun/02/01-01	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.050	445.9	19.82	19.43
	Jun/02/01-02	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.100	426.7	18.98	
	Jun/02/01-03	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.250	438.5	19.50	
2	Jun/02/01-04	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.050	455.9	20.26	20.03
	Jun/02/01-05	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.100	441.7	19.64	
	Jun/02/01-06	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.250	453.5	20.17	
3	Jun/02/01-07	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.050	464.9	20.66	20.31
	Jun/02/01-08	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.100	456.7	20.31	
	Jun/02/01-09	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.250	448.5	19.95	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. ★ Bangalore

Authorized Signatory

CONSULTING ENGINEER Bangalore

Sunitha.N.K
AE&IO

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/05/01/01/2020-21 Date:09.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/05/02
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	05.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
4	Jun/02/01-10	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.050	445.9	19.82	19.43
	Jun/02/01-11	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.100	426.7	18.98	
	Jun/02/01-12	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.250	438.5	19.50	
5	Jun/02/01-13	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.050	455.9	20.26	20.03
	Jun/02/01-14	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.100	441.7	19.64	
	Jun/02/01-15	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.250	453.5	20.17	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

CONSULTIG ENGINEER Pvt. Ltd. Bangalore

Smitha. N L
AE WO

Page 2/2

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Scanned with CamScanner

Report No:SCEPL/MT/Jun/05/01/01/2020-21

Date:30.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/05/01
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	05.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	Jun/02/01-16	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.12
	Jun/02/01-17	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.100	680.7	30.27	
	Jun/02/01-18	02.06.2020	30.06.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
2	Jun/02/01-19	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.050	669.9	29.77	29.84
	Jun/02/01-20	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.100	672.7	29.92	
	Jun/02/01-21	02.06.2020	30.06.2020	149.9	150.0	149.8	22485	8.250	670.5	29.82	
3	Jun/02/01-22	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.050	670.9	29.82	30.13
	Jun/02/01-23	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.100	692.7	30.81	
	Jun/02/01-24	02.06.2020	30.06.2020	149.9	150.0	149.8	22485	8.250	669.5	29.78	

Remarks:-

The results pertain to the samples received and tested.
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate
* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

BVH CONSULTIG ENGINEER Pvt Ltd Bangalore

AE WD

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli Bangalore-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama88@gmail.com

Scanned with CamScanner

Report No:SCEPL/MT/Jun/05/01/01/2020-21 **Date:30.06.2020**

TEST REPORT

***Client Name& Address:**	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
***Name of Work:**	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
***Letter Reference:**	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/05/02
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	05.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
***Grade of concrete**	M30
***Location**	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
4	Jun/02/01-25	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.12
	Jun/02/01-26	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.100	680.7	30.27	
	Jun/02/01-27	02.06.2020	30.06.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
5	Jun/02/01-28	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.050	669.9	29.77	29.84
	Jun/02/01-29	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.100	672.7	29.92	
	Jun/02/01-30	02.06.2020	30.06.2020	149.9	150.0	149.8	22485	8.250	670.5	29.82	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

CONSULTING ENGINEERS Bangalore

Smitha. N L
AE W10

Page 1/1

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Scanned with CamScanner

Report No:SCEPL/MT/Jun/12/01/01/2020-21

Date:17.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/12/01
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	12.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	Jun/10/01-01	10.06.2020	17.06.2020	150.0	150.0	149.9	22500	8.050	426.7	18.96	19.58
	Jun/10/01-02	10.06.2020	17.06.2020	150.0	149.9	150.0	22485	8.100	438.5	19.50	
	Jun/10/01-03	10.06.2020	17.06.2020	149.9	150.0	149.8	22485	8.250	455.9	20.28	
2	Jun/10/01-04	10.06.2020	17.06.2020	150.0	150.0	149.9	22500	8.050	441.7	19.63	20.16
	Jun/10/01-05	10.06.2020	17.06.2020	150.0	149.9	150.0	22485	8.100	453.5	20.17	
	Jun/10/01-06	10.06.2020	17.06.2020	149.9	150.0	149.8	22485	8.250	464.9	20.68	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

CONSULTING ENGINEERS PVT. LTD. BYH Bangalore

Suvitha .N.L
AE W/O

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama88@gmail.com

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/12/01/01/2020-21 **Date:17.06.2020**

TEST REPORT

***Client Name& Address:**	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
***Name of Work:**	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
***Letter Reference:**	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/12/02
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	12.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
***Grade of concrete**	M30
***Location**	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
3	Jun/10/01-07	10.06.2020	17.06.2020	150.0	150.0	149.9	22500	8.050	460.9	20.48	20.47
	Jun/10/01-08	10.06.2020	17.06.2020	150.0	149.9	150.0	22485	8.100	459.7	20.44	
	Jun/10/01-09	10.06.2020	17.06.2020	149.9	150.0	149.8	22485	8.250	460.5	20.48	
4	Jun/10/01-10	10.06.2020	17.06.2020	150.0	150.0	149.9	22500	8.050	470.9	20.93	20.81
	Jun/10/01-11	10.06.2020	17.06.2020	150.0	149.9	150.0	22485	8.100	472.7	21.02	
	Jun/10/01-12	10.06.2020	17.06.2020	149.9	150.0	149.8	22485	8.250	460.5	20.48	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

SHIPRAMA CONSULTIG ENGINEERS PVT. LTD. Bangalore

AE/JD

Assistant Executive Engineer
Vidyaranyapur 1 Sub Division
BBMP, Bangalore-97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli Bangalore-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/12/01/01/2020-21 **Date:08.07.2020**

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Doddabommasandra Old village , Subbanna Beedi and Surrounding areas in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/208/2019-20 Dated- 10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/12/01
Agency	KIRDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	05.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	Jun/10/01-13	10.06.2020	08.07.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.12
	Jun/10/01-14	10.06.2020	08.07.2020	150.0	149.9	150.0	22485	8.100	680.7	30.27	
	Jun/10/01-15	10.06.2020	08.07.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
2	Jun/10/01-16	10.06.2020	08.07.2020	150.0	150.0	149.9	22500	8.050	669.9	29.77	29.84
	Jun/10/01-17	10.06.2020	08.07.2020	150.0	149.9	150.0	22485	8.100	672.7	29.92	
	Jun/10/01-18	10.06.2020	08.07.2020	149.9	150.0	149.8	22485	8.250	670.5	29.82	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

SHIPRAMA CONSULTING ENGINEERS PVT LTD Bangalore

AE/JE

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

#.1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com

Scanned with CamScanner